

# Acrylic Modified Alkyds

Products	% NVM (Volatile/ solvent)	Acid value (mg KOH/ gm)	Color Gardner	Viscosity BF @ 25°C	Viscosity Gardner @25°C	Oil %	%PA (Approx)	Description / Uses
S 35605SN	60.0 +/-1.0 (SN 150)	7.0 max	3.0 max	25.0 - 35.0	Z1 - Z2	39.0 - 41.0	15.0 - 17.0	Acrylated modified alkyd resin for pigmented roller coating enamels and baking system.
S 35751M	75.0 +/- 1.0	2.0 max	5.0 max	-	Z5 - Z6	39.0 - 41.0	15.0 - 17.0	Acrylated modified alkyd resin for general industrial direct-metal enamels, top coat and agriculture implements.