

# Urethane Modified Alkyds

Products	% NVM (Volatile/solvent)	Acid value (mg KOH/gm)	Color Gardner @ solids	Viscosity B4 F/C@30°C (%Solids WS)	Viscosity Poise/ Gardner @25°C	Oil Type	%Oil (approx)	Isocyanate Type / %	Description / Uses
S 60551WS	55.0+/-1.0 (WS)	2.0 max	6.0 max (as such)	-	X - Z	Veg. oil / Fatty acid	60.0+/-1.0	Aromatic 15.0 Max	General purpose urethane alkyd with good abrasion resistance and good drying properties.
S 60553WS	55.0+/-1.0 (WS)	2.0 max	6.0 max (45.0 %)	90.0 - 120.0 Sec (45.0%)	Z6 +	Veg. oil / Fatty acid	60.0 +/-1.0	Aromatic 15.0 Max	Single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/ floor coatings and exclusively for interior coatings.
S 60553LVWS	55.0+/-1.0 (WS)	2.0 max	6.0 max (as such)	-	11.0 - 14.0 Ps	Veg. oil / Fatty acid	60.0 +/-1.0	Aromatic 15.0 Max	Low viscosity, single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/floor coatings and exclusively for interior coatings only.
S 60553HVWS	55.0+/-1.0 (WS)	2.0 max	6.0 Max (45.0%)	130.0 - 150.0 Sec (45.0%)	-	Veg. oil / Fatty acid	60.0+/-1.0	Aromatic 15.0 Max	High viscosity single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/floor coatings and exclusively for interior coatings.
S 60601LVWS	60.0 +/-1.0 (WS)	2.0 max	6.0 max (as such)	-	45.0-65.0 Ps @ 25 °C	Veg. oil / Fatty acid	60.0 +/-1.0	Aromatic 15.0 Max	High solid, single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/floor coatings and exclusively for interior coatings only.
S 60601HVWS	60.0 +/-1.0 (WS)	2.0 max	6.0 max (50.0%)	250.0 - 300.0 Sec (50.0%)	1500.0 +/- 350.0 Ps	Veg. oil / Fatty acid	60.0 +/-1.0	Aromatic 15.0 Max	High solid, single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/floor coatings and exclusively for interior coatings only.
S 60603ExtWS	60.0 +/-1.0 (WS)	2.0 max	6.0 max (50.0%)	50.0 - 65.0 Sec (50.0%)	40.0-65.0 Ps	Veg. oil / Fatty acid	60.0 +/-2.0	Aliphatic 15.0 Max	Single pack having good air drying with excellent gloss and abrasive resistance recommended for wood finishes, parquet/ floor coatings and exclusively for exterior coatings only.