

Vinyl Esters

Products	Color / Clarity	% NVM (Volatile/ solvent)	Viscosity B/F @ 25°C / cPs	Gel time @25°C/ Min	Description / Uses
VE 90606NA	Yellow Clear	55.0 - 60.0 (Styrene)	400.0 - 600.0	10.0 - 15.0	Specially designed for hand lay-up and filament winding applications.